

FENDA GUARD™

Technical Specifications

| | | |
|--------------------------------|---|------------|
| Description: | Natural Cork® Fenda Guard™ crack suppression membrane | |
| Installation: | Glue Down | |
| Sizes: | 48.25" x75' | |
| Thickness: | 1.2mm | |
| Composition: | Homogenous 100% quercus suber cork composition with recycled rubber | |
| Anti-allergenic | Cork- quercus suber is a bacteria and spore resistant product | |
| Insect Resistance | Cork- quercus suber is a natural insect | |
| Anti-microbial | inhibits mold and bacteria in binder | |
| Binder | Polymeric | |
| Cork Granule Size (mm) | 0.5/1 | |
| Color | Black | |
| Physical Characteristics | | |
| Density | > 0.48 | |
| Compressibility at 400 PSI (%) | 20-40 | |
| Recovery after (%) | > 70 | |
| Tensile strength (Kg/cm) | | |
| Transversal direction | > 8 | |
| Longitudinal direction | > 12 | |
| Flexibility | | |
| Original (F5) | No cracks | |
| | ASTM n° 1 Oil, 70 hrs @ 100° C (F16) | No cracks |
| | Oven aged, 70 hrs @ 100° C (F16) | No cracks |
| Volume Change after Immersion | | |
| | ASTM n° 1 Oil, 70 hrs @ 100° C (%) | -5 to +15 |
| | ASTM n° 3 Oil, 70 hrs @ 100° C (%) | +15 to +50 |
| | ASTM Fuel A, 22 hrs @ 23° C (%) | -5 to +15 |

Ergonomic acclaim Healthier Choice – Anti-microbial
 Forever Resilient
 Warm and Soft Underfoot
 Acoustical values
 Contributes to Productivity in the Workplace
 Shock/Impact Absorption

Sustainable acclaim Pre-Consumer / Post-Industrial cork product 100%
 Rapidly Renewable Resource 100%
 Formaldehyde-free